

Spray

Product properties

Heat resistant spray paint for surfaces exposed to very high temperatures.
Heat resistant up to 800 °C.

Product use

Used for the treatment of, among others, log burners and fireplaces, as well as other small metal surfaces.



Substrate

Must be clean, dry, free of grease and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning and sanding.
Dirt, grime, grease and spills are removed by cleaning.
Sand hard, smooth surfaces.

Application

Shake for two minutes before use.
Test on small area to check adherence and the result.
Spraying distance 25 - 30 cm.
Working temperature 15 - 25°C.
Apply in several thin layers.
After one hour of drying, the piece is heated for 30 to 60 minutes (160°C) so that the varnish hardens.
After use, turn the can upside down and spray for several seconds.

Good practise

Carefully cover surfaces and areas that are not to be painted.
Smoke is produced during the hardening process.
Ensure good ventilation.

Expected result

Glossy covered surface.
Resistant to dusting and light wiping with a damp cloth.
Carefully load the surface until the paint is completely hardened.

Environmental information

Clean off the paint from tools before cleaning. Bring remains of fluent paint to the local recycling centre. Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage: Cool, frost-free and tightly closed

Technical Data

Gloss	Gloss
Solids Weight %	9.7
Min. working temp. during application and drying/curing	Min. +15°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Fully cured at 20° C, 60 % RH (Days)	1

Current TDS Version

January 2022