

# Floor Varnish

### **Properties**

Semi-matt, PU reinforced acrylic floor varnish. Rich with good coalescence, extra durability and scratchproof.

### Use

For all types of wood in living rooms, corridors, entries, stairwells, offices and kitchens. The surface must be treated with varnish primer or have been previously varnished.



### **Substrate**

Must be clean, dry, firm and suitable for surface treatment.

#### **Treatment**

Remove uneven or peeling varnish and paint completely down to the clean wood by sanding.

Prime untreated wood using Floor Primer.

Clean existing varnish for dirt, grease and wax using Wood Cleaner.

Sand to matt finish but not too deep.

Vacuum clean and dry with a hard-wrung cloth.

Best durability is achieved with 2 or more treatments.

# **Application**

Brush or roller.

Decide on your mode of application according to the desired finish.

Apply wet on wet and finish by brushing/rolling in the same direction, avoid overlap and varnish-pools.

Always use the same batch number on contiguous/unbroken surfaces.

Differences in surface structure can result in a deviation in gloss.

Cold/heat can affect the viscosity of the material.

Condensation must be prevented during drying/curing.

Cold and increased humidity extends drying time, full curing and recoat interval.

Increased temperature and low atmospheric humidity reduce drying time and full curing.

Wood floors must have balanced moisture when undergoing treatment.

Check adhesion by pressing a coin perpendicularly against the varnished surface.

Always perform a test treatment for a check and acceptance of adhesion and result

## **Expected result**

Semi-matt, colourless, extra durable, robust and scratchproof.

Rich finish with optimal coalescence.

Withstands general wear and tear and cleaning with a universal cleaning agent and a wrung cloth.

Does not prevent any discolouration from the lignin or tannin in the wood.

Exercise care in loading the surface until the varnish is fully cured.

The surface can be used after 24 hours.

### **Environmental information**

Cleaning of tools: Remove as much paint as possible before cleaning with water and soap.

Storage: Cool and frost-free.

NB! See also Product Datasheet.

Storage: Cool, frost free and tightly closed

# **Technical Data**

Product Type [9]  Gloss 25;Semi Matte  Density (kgs/l) 1.03  Nominal spreading rate (m²/ltr.) 8  Drying time at 20° C, 60 % RH (Hours) 1  Recoatable at 20° C, 60 % RH (Hours) 3  Fully cured at 20° C, 60 % RH (Days) 28  Dilution Do not dilute, cannot be tinted  Cleaning of Tools etc. Water and soap		
Density (kgs/l)  Nominal spreading rate (m²/ltr.)  8  Drying time at 20° C, 60 % RH (Hours)  1  Recoatable at 20° C, 60 % RH (Hours)  3  Fully cured at 20° C, 60 % RH (Days)  Do not dilute, cannot be tinted	oduct Type	[9]
Nominal spreading rate (m²/ltr.)  Drying time at 20° C, 60 % RH (Hours)  1  Recoatable at 20° C, 60 % RH (Hours)  3  Fully cured at 20° C, 60 % RH (Days)  Do not dilute, cannot be tinted	iss	25;Semi Matte
Drying time at 20° C, 60 % RH (Hours)  Recoatable at 20° C, 60 % RH (Hours)  3  Fully cured at 20° C, 60 % RH (Days)  28  Dilution  Do not dilute, cannot be tinted	nsity (kgs/l)	1.03
Recoatable at 20° C, 60 % RH (Hours)  Fully cured at 20° C, 60 % RH (Days)  28  Dilution  Do not dilute, cannot be tinted	minal spreading rate (m²/ltr.)	8
Fully cured at 20° C, 60 % RH (Days)  28  Dilution  Do not dilute, cannot be tinted	ring time at 20° C, 60 % RH (Hours)	1
Dilution Do not dilute, cannot be tinted	coatable at 20° C, 60 % RH (Hours)	3
<u> </u>	ly cured at 20° C, 60 % RH (Days)	28
Cleaning of Tools etc. Water and soap	ution	Do not dilute, cannot be tinted
	eaning of Tools etc.	Water and soap

## **Current TDS Version**

December 2021

### **Replaces TDS Version**

January 2021