

Repa Quick 20

Properties

Fast-drying filler powder for indoor repairs and filling on plaster, concrete, gypsum boards etc. In dry form, polymer-reinforced plaster is soluble in water.



- Easy to mix
- Good filling capacity
- Doesn't sink

Use

For interior use for repairs on concrete, gypsum board, glass felt etc.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning, sanding and dusting.

Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37.

Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49.

Sand flat hard, slippery surfaces.

Apply the filler paste and smooth out.

Sand the surface and prime it before any additional treatment.

Application

Apply and smooth out using a filler knife.

Decide your choice of tools based on the size of the surface.

Mixing: 1 part water and 2 parts powder.

Pour water in a bucket and sprinkle in the powder.

Leave for 3-5 minutes before stirring.

Apply a sufficient amount and then work and smooth out the filler paste.

Cold/ heat can affect the viscosity of the material.

Condensation must not occur.

Cold and increased humidity extends drying time, full curing and recoat interval

Increased temperature and low atmospheric humidity reduce drying time and full curing

Always perform a test treatment for a check and acceptance of adhesion and result

Expected result

Smooth out surface for additional treatment.

Environmental information

Remove as much filler as possible before cleaning with water. Bring remains of fluent paint to the local recycling centre.

Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage: Cool, frost-free, and tightly closed

Technical Data

Product Type	Plaster & Sealant
Color (plaster)	White
Mixture proportion	2 parts powder : 1 part water
m/l, depending on joint width and depth	1
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Recoatable at 20° C, 60 % RH (Hours)	1
Layer thickness (max. Mm)	50
Dilution	Water
Cleaning of Tools etc.	Water

Current TDS Version

December 2021

Replaces TDS Version

October 2020